

■ **IBUpart®**

Product Portfolio

HIGH QUALITY MATERIALS FOR
POLISHING AGENTS, COSMETICS,
LACQUER APPLICATIONS AND MORE



IBU-tec

IBU-tec is a leading specialist for rotary kilns, pulsation reactors and thermal process engineering in general. Extensive know-how with materials for a wide variety of end uses comes from over 50 years of experience with polishing agents made from rare earths to colorless UV-absorbing materials and tailor-made catalysts.

Product Portfolio

IBUpart® Al₂O₃ ALUMINIUM(III)-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) μm	Purity (%)
150 ± 5	20 - 40	0.3 - 0.5	> 99
30 ± 5	n/a	< 10.0	> 99

Potential applications: polishing agents, catalyst supports, ceramics

IBUpart® CeO₂ CERIUM(IV)-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) μm	Purity (%)
40 ± 2	15 - 20	10.0 - 20.0	> 99
2 ± 1	n/a	1.5 - 2.0	85 - 98

Potential applications: polishing agents, catalysts, UV-absorbers

IBUpart® Fe₂O₃ IRON(III)-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) μm	Purity (%)
40 ± 2	35 - 40	5.0 - 10.0	> 99

Potential applications: corrosion protection, catalysts, lubricants, battery material

IBUpart® Y-AlO₃ YTTRIUM-ALUMINIUM-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) μm	Purity (%)
12 ± 2	100 - 1000	1.0 - 2.0	> 99

Potential applications: light sources, LEDs, lasers

IBUpart® ZnO

ZINC(II)-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) µm	Purity (%)
60 ± 5	12 - 15	0.2 - 0.3	> 99
35 ± 2	20 - 25	0.3 - 0.4	> 99
20 ± 2	20 - 50	0.4 - 0.5	> 99

Potential applications: UV-absorbers, pigments, cosmetics, lacquers

IBUpart® ZrO₂

ZIRCONIUM(IV)-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) µm	Purity (%)
70 ± 5	15 - 20	0.3 - 0.5	> 99
30 ± 5	30 - 70	1.0 - 5.0	> 99

Potential applications: grinding and polishing agents, 3D printing

IBUpart® Y-ZrO₂

YTTRIUM-STABILIZED ZIRCONIUM(IV)-OXIDE

Specific surface area (BET) m ² /g	Primary particle size (TEM) nm	Agglomerate size (d50) µm	Purity (%)
70 ± 5	15 - 20	0.3 - 0.5	> 99

Potential applications: ceramics, bioceramic implants

CUSTOMIZED PRODUCTS

Standard specifications and materials are given in the tables above.

- If desired, we can optimize these to be customer-specific and adapt the parameters to your requirements.
- Further oxides and dopings can be produced upon request.
- Suspensions with different specifications can also be created.

Please contact us for more information!

Email: mail@jibu-tec.com | Phone: +49 - 3643 - 8649 - 0

Imprint

IBU | tec

IBU-tec advanced materials AG

Hainweg 9-11

99425 Weimar

Germany

Phone: +49 (0) 3643 8649-0

Fax: +49 (0) 3643 8649-30

Mail: mail@ibu-tec.com

Internet: www.ibu-tec.com